

Comparative Study on the Effects of Steel Slag Aggregate over Blended Cement Concrete

Mayur Jain¹ Sachin Jat²

^{1,2}Department of Civil Engineering

^{1,2}SIRTE Bhopal, India

Abstract— Concrete is the most versatile construction material because it can be designed to withstand the harshest environments while taking on the most inspirational forms. Engineers are continually pushing the limits to improve its performance with the help of innovative chemical admixtures and alternative construction materials (ACM). Nowadays, most concrete mixture contains alternative construction materials which form part of the cementitious component. These materials are majority byproducts from other processes. The main benefits of ACM (alternative construction materials) are their ability to replace certain amount of cement or aggregates and still able to display major properties similar to concrete, thus reducing the cost of using traditional materials. The fast growth in industrialization has resulted in tons and tons of byproduct or waste materials, which can be used as ACMs (alternative construction materials) such as marble powder, silica fume, ground granulated blast furnace slag, steel slag etc. The use of these byproducts not only helps to utilize these waste materials but also enhances the properties of concrete in fresh and hydrated states. Most concrete produced today includes one or more ACM (alternative construction materials). For this reason, their properties are frequently compared to each other by mix designers seeking to optimize concrete mixtures. To design high strength concrete good quality aggregates is also required. Steel slag is an industrial byproduct obtained from the steel manufacturing industry. This can be used as aggregate in concrete. It has been usually used as aggregate in hot mix asphalt surface applications, but in the present work it has been used in conventional concrete mixture and performance is compared with normal aggregate concrete. Replacing all or some portion of natural aggregates with steel slag would lead to considerable environmental benefits. Steel slag aggregate generally exhibit a propensity to expand hence steel slag aggregates are generally not used in concrete making. However, use of blended cement concrete is reported to reduce the expansion of the concrete. In the present work a series of tests were carried out to make comparative studies of various mechanical properties of concrete mixes prepared by using normal cement concrete, marble powder and cement blend concrete (1:1 proportion) with or without use of steel slag. The ingredients are mixed in 1: 1.5: 3 proportions. The properties studied are 7 days, 14 days and 28 days compressive strengths, workability and surface hardness.

Keywords: Cement, Concrete, Steel Slag, Aggregates, Blended Cement, Marble Powder

I. INTRODUCTION

A. Background

Concrete is a fusion of cement, coarse aggregate, fine aggregates and water. Its success lies in its adaptability as can be designed to resist cruel environments although taking on the most inspirational forms. Scientists and Engineers are

further aiming to enhance its limits with the help of novel chemical admixtures and various Alternative construction materials (ACMs).

Previously ACMs (Alternative construction materials) comprises of readily available materials, natural like diatomaceous earth or volcanic ash. The engineering marvels like Roman aqueducts, the Coliseum are examples of this practice used by Romans and Greeks. Currently, the majority concrete mixture consists ACMs (Alternative construction materials) which are mainly by-product or waste materials from other industrial processes.

B. Marble Powder as ACM

The development of concrete technology can decrease the use of natural resources and energy sources and lowers the load of pollutants on atmosphere. Currently huge amount of marble dust is produced in natural stone processing plants with a significant impact on environment and human beings. In building industry, Marble has been frequently used for different purposes like cladding, flooring, etc. The industrial removal of the marble powder material is in the form of a fine powder and constitutes as one of the atmospherically problems in the world. In India, marble dust is settled by sedimentation and then dumped away, results in environmental pollution. In addition to form dust in summer, threats both public health and agriculture. Therefore, consumption of the marble dust in various firms especially in construction, agriculture, paper and glass industries helps to protect the surroundings. Some measures have been taken to assess the chances of using waste marble powder in concrete and mortars and results of strength and workability were evaluated with control samples of traditional cement concrete. Some measures have been taken to assess the chances of using waste marble powder in concrete and mortars and results of strength and workability were evaluated with control samples of traditional cement concrete.



Fig. 1: Marble Powder

C. Steel Slag

Steel slag is a derivative of steel manufacturing, is generated during the separation of molten steel from impurities in steel production furnaces. These can be utilized as aggregate in concrete. Steel slag aggregate usually shows a tendency to

swell because of the existence of magnesium oxides and free lime that have not reacted with the silicate structure and that can hydrate and swell in moist atmosphere. This potentially expansive nature (volume transforms up to 10 % or more attribute able to the hydration of calcium oxide and magnesium) might originates complexity with products including steel slag, and is one reason why steel slag aggregate is not used in concrete. Steel slag is presently used as aggregate in hot mix asphalt surface purposes, but there is a call for some supplementary work to resolve the possibility of utilizing this industrial derivative more wisely as a substitute for both fine and coarse aggregates in a traditional concrete mixture. Maximum volume of concrete contains aggregates. Substituting all or some fraction of natural aggregates with steel slag would lead to substantial environmental benefits. Steel slag has more specific gravity, high abrasion value than normal aggregates apart from the disadvantages such as high-water absorption, high alkalis. Consequently, with appropriate treatments it can be utilized as coarse aggregate in concrete.



Fig. 2: Steel Slag

Physical properties of Steel slag - The special physical properties of steel slag are provided below in Table

Material	Specific gravity	Water absorption in %
Steel slag	3.35	1.1%

Table 1: Physical Properties of Steel Slag

D. Objective of Present Study

The major motivation of this project is the increase in waste products consumption's and decrease consumption of cement in construction industry. By decreasing the use of cement and natural aggregates, cost of construction may be reduced and it also reduces the environmental hazards produced by cement. The emphasis of researcher is to investigate the suitability of waste materials such as marble powder, and steel slag as alternative construction material. These materials are used to form concrete mix and are compared on the following parameters –

- 1) Compressive strength after 7, 14 and 28 days
- 2) Workability

Objectives of the present study are summarized as following:

- 1) To study the suitability of various waste materials in the construction industry.
- 2) To assess the effects of replacing cement and aggregates with waste materials over different properties.

II. EXPERIMENTAL WORK

A. Mix Design of Concrete

Experimental work had been conducted on cement concrete mixes by using different type of binder mix modified with

different percentages of steel slag in partial replacement of gravels as aggregates. Two separate types of concrete mixes were prepared in first category ordinary cement has been used and in second category blended cement with 1:1 ratio of cement and marble powder has been used. For each category of binder mix steel slag replaced coarse aggregates in several different proportions such as 5%, 10%, 15%, 20% and 25% by weight. For each replacement several cubes have been casted for determining the compressive strength and workability. For each replacement 3 cubes have been casted and average value of measured quantity has been considered.

Type of aggregate affects the several physical and chemical properties of the concrete and mortar. Here in the present work, several properties of concrete such as compressive strength and workability are identified and evaluated for investigating the effect of aggregates on the structural behavior and performance of concrete. From several available tests to determine the quality of the concrete, compression test has been identified as the utmost chief which gives an idea about all the characteristics of concrete. By this single test one judge that whether Concreting has been done properly or not. For cube test two types of specimens either cubes of 15 cm X 15 cm X 15 cm or 10cm X 10 cm x 10 cm depending upon the size of aggregate are used. In the preparation time of cube firstly do sieve analysis test -

B. Sieve Analysis of Sand

The Sieve Analysis of sand is carried out to know the zone of the sand. The results of sieve analysis are given in Table

Sieve size	Weight Retained in gm	% Passing
4.75 mm	16 gm	98.4
2.36 mm	11 gm	97.3
1.18 mm	65 gm	90.8
600 microns	391 gm	51.6
300 microns	420 gm	9.4
150 microns	82 gm	1.2
Total		-

Table 2: Result of sieve analysis of sand

C. Physical Properties of Sand

Before starting laboratory experimental work, the physical properties like specific gravity and water absorption sand have been determined. The physical properties of sand obtained are given below in Table No 4.2.

Fine aggregate	Specific gravity	Water absorption %
Sand	2.65	0.6

Table 3: Properties of sand

In the present work cubical moulds of size 15 cm x 15cm x 15 cm have been used to cast the concrete cubes for testing. This size of the cube is as per the IS 10086 – 1982. These specimens are tested by compression testing machine after 7 days, 14 days and 28 days of curing. In the present study concrete mix of grade M20 has been considered. Weight of the ingredients such cement, sand, gravel and water has been presented in Table 4.3. It has been seen that water cement ratio has been considered as 0.5 for optimum consistency. Blended cement with cement to marble powder ratio as 1:1 has been considered in this study.

Water	Cement/ Blended Cement (1:1)	Coarse aggregate	Sand
1.5	4	12	6

Table 4: Proportion of all the ingredients in prepared mix of 1:1.5:3 in Kg

Category of Mix	Mixno.	Ingredients (Kg)					
		Cement	Marble Powder	Sand	Coarse Aggregate	Steel Slag	% Steel Slag
C1 (Plain cement concrete)	C100	4	0	6	12	0	0
	C105	4	0	6	11.4	0.6	5
	C110	4	0	6	10.8	1.2	10
	C115	4	0	6	10.2	1.8	15
	C120	4	0	6	9.6	2.4	20
	C125	4	0	6	9.0	3.0	25
C2 (Blended cement concrete)	C200	2	2	6	12	0	0
	C205	2	2	6	11.4	0.6	5
	C210	2	2	6	10.8	1.2	10
	C215	2	2	6	10.2	1.8	15
	C220	2	2	6	9.6	2.4	20
	C225	2	2	6	9.0	3.0	25

Table 5: Concrete mixes prepared with variation in Steel Slag Aggregates




Fig. 3: weight of ingredients in C1 category mix




Fig. 4: weight of ingredients in C2 category mix

D. Process for Preparing Cubes

In cube preparation time firstly prepare batching of ingredients of concrete. All ingredients proportion given in the table 4.3 then after mixing and in one ratio prepare three cubes of same proportion, each cube fills up in three layers. Each layer tamping 25 times by tamping rod, after one day remove cube from mould and drying it in room temperature.

After drying process of cubes then do compression test by Universal testing machine, in 7,14 and 28 days of each cube. In this test input data by computer then show result in the screen.

E. Workability

The behavior of fresh concrete after mixing up to compaction depends mainly on the characteristics which is workability. Workability of concrete is a term which includes for parameters which are Mixability, Transportability, Mouldability and Compatibility. For the determination of workability there are three methods first is Vee-Bee consistometer test, second is compaction test and last is slump cone test. In this research work using last method slump cone test. The slump is a measure indicating the consistency or workability of cement concrete. Slump test can be conducted before or during the advancement of project in the field for assessing the consistency of concrete where ostensible maximum size of aggregate has been restricted to 40 mm. This test performs in every proportion of ingredients, height of cone 30cm, top and bottom diameter 10 cm and 20 cm respectively. Cone fills in three layer and each layer tamped three times by tamping rod. After filling of cone then remove frame and measure slump by measuring rod. After removing cone then three types slump shear, collapse and true. If slump true then take reading. From collection of materials to analysis of results presents the methodology of the present work. This research has been divided in separate steps. Following Flow chart will present the methodology involved in the present work.




Fig. 5: Flow chart of Methodology

III. RESULTS AND DISCUSSION

A. Results of 7 days Compressive strength

After testing of cubes in 7, 14 and 28 days by Universal testing machine and results shows in table

S. No.	Mix no.	Cube 1	Cube 2	Cube 3	Average
1	C100	13.2	13.3	13.2	13.23
2	C105	13.5	13.6	13.6	13.57
3	C110	13.9	14.2	14.1	14.07
4	C115	14.8	15	15.1	14.97
5	C120	15.1	15.4	15.2	15.23
6	C125	15.4	15.4	15.5	15.43
7	C200	13.8	13.9	14.2	13.97
8	C205	14.3	14.5	14.6	14.47
9	C210	15.1	15.3	15.1	15.17
10	C215	15.6	15.9	15.8	15.77
11	C220	16.6	16.8	16.8	16.73
12	C225	17.1	17.2	17.1	17.13

Table 6: Results of 7 days Compressive strength




Fig. 6: 7 days compressive strength of C1 (ordinary Portland cement) category mix




Fig. 7: 7 days compressive strength of C2 (Blended cement) category mix

B. Results of 14 days Compressive strength

S. No.	Mix no.	Cube 1	Cube 2	Cube 3	Average
1	C100	15.8	15.7	15.9	15.80
2	C105	16.6	16.4	16.6	16.53
3	C110	16.9	17	16.7	16.87
4	C115	17.4	17.6	17.6	17.53
5	C120	17.8	18.2	18.1	18.03
6	C125	18.4	18.7	18.4	18.50
7	C200	16.5	16.3	16.5	16.43
8	C205	17.1	16.9	17.3	17.10
9	C210	17.6	17.5	17.7	17.60
10	C215	18.1	18.3	18	18.13
11	C220	18.9	18.8	18.7	18.80
12	C225	19.6	19.4	19.8	19.60

Table 7: Results of 14 days Compressive strength




Fig. 8: 14 days compressive strength of C1 (ordinary Portland cement) category mix




Fig. 11: 28 days compressive strength of C2 (Blended cement) category mix




Fig. 9: 14 days compressive strength of C2 (Blended cement) category mix

C. Results of 28 days Compressive strength

S. No.	Mix no.	Cube 1	Cube 2	Cube 3	Average
1	C100	19.2	19.3	19.2	19.23
2	C105	19.7	19.5	19.4	19.53
3	C110	20.2	20.4	20.3	20.30
4	C115	20.8	20.7	20.8	20.77
5	C120	21.1	21.3	21.4	21.27
6	C125	21.6	21.6	21.8	21.67
7	C200	19.6	19.7	19.9	19.73
8	C205	20.3	20.4	20.4	20.37
9	C210	20.8	20.9	20.8	20.83
10	C215	21.5	21.7	21.6	21.60
11	C220	21.9	21.8	22.1	21.93
12	C225	22.4	22.7	22.5	22.53

Table 8: Results of 28 days Compressive strength




Fig. 10: 28 days compressive strength of C1 (ordinary Portland cement) category mix

D. Results of Slump Cone Test

S. No.	Mix no.	Slump Value (mm)
1	C100	97
2	C105	92
3	C110	86
4	C115	78
5	C120	74
6	C125	68
7	C200	108
8	C205	102
9	C210	94
10	C215	87
11	C220	81
12	C225	73

Table 9 – Results of Slump Cone Test



Fig. 12: Slump value in mm for C1 (ordinary Portland cement) category mix




Fig. 13: Slump value in mm for C2 (blended cement) category mix

IV. CONCLUSIONS AND FUTURE SCOPE

A. Conclusions

In the present work marble powder and steel slag have been investigated as alternate cementitious materials. Concrete mixes have been prepared by replacing cement with these materials in different percentage, thereafter, their compressive strength and slump values are determined and compared with ordinary Portland cement concrete values. Two categories of concrete mixes C1(ordinary blended cement) and C2(blended cement) have been prepared in C1(ordinary blended cement) category ordinary cement has been used and in C2 (blended cement) category blended cement with 1:1 ratio of cement and marble powder has been used. Following are the conclusions of the present work

- 1) Suitability of waste materials such as marble powder, and steel slag as alternative construction material has been investigated.
- 2) The concrete mixes formed by using above materials have been tested for Compressive strength after 7, 14 and 28 days and Workability.
- 3) Concrete mix of grade M 20 has been considered for performing the present study.
- 4) Water cement ratio has been considered as 0.5 for optimum consistency.
- 5) Two categories of concrete mixes have been prepared in first category ordinary cement has been used and in second category blended cement with 1:1 ratio of cement and marble powder has been used.
- 6) In each category steel slag replaced coarse aggregates in 5 different percentage 5%, 10%, 15%, 20% and 25% by weight. For each replacement 3 cubes have been casted and average value of measured quantity has been considered.
- 7) Strength of concrete increases with the increase in proportion of steel slag in concrete.
- 8) Slump value reduces with the increase in the proportion of steel slag.
- 9) In C1 (ordinary blended cement) category compressive strength increases rapidly when content of steel slag is more than 15%. However, for C2(blended cement) category mixes, development of strength is very high even with low proportion of steel slag, when compared to C1(ordinary blended cement) category mixes. In C1(ordinary blended cement) and C2 (blended cement) category compressive strength increase rapidly up-to 15% content of steel slag. Moreover, for C2 (blended cement) category mixes, development of strength is more than C1 (ordinary blended cement) category mixes.
- 10) Slump value for C1(ordinary blended cement) category mixes is lower than slump of C2(blended cement) category. Workability of both the category mixes decreases with the enhancement in the proportion of steel slag.

B. Future Scope

To investigate the appropriateness and effectiveness of alternative materials in civil engineering works and materials, as a replacement to chief constituents, further more results have been required.

- 1) This work can be extended for high grade of concrete.

- 2) Mix design of concrete by using other waste materials.

REFERENCES

- [1] Bernal, S., De Gutierrez, R., Delvasto, S., & Rodriguez, E. (2010). Performance of an alkali-activated slag concrete reinforced with steel fibers. *Construction and Building Materials*, 24(2), 208-214.
- [2] Qasrawi, H., Shalabi, F., & Asi, I. (2009). Use of low CaO unprocessed steel slag in concrete as fine aggregate. *Construction and Building Materials*, 23(2), 1118-1125.
- [3] Boukendakdji, O., Kenai, S., Kadri, E. H., & Rouis, F. (2009). Effect of slag on the rheology of fresh self-compacted concrete. *Construction and Building Materials*, 23(7), 2593-2598.
- [4] Wu, S., Xue, Y., Ye, Q., & Chen, Y. (2007). Utilization of steel slag as aggregates for stone mastic asphalt (SMA) mixtures. *Building and Environment*, 42(7), 2580-2585.
- [5] Gonen, T., & Yazicioglu, S. (2007). The influence of mineral admixtures on the short and long-term performance of concrete. *Building and Environment*, 42(8), 3080-3085.
- [6] Maslehuddin, M., Sharif, A. M., Shameem, M., Ibrahim, M., & Barry, M. S. (2003). Comparison of properties of steel slag and crushed limestone aggregate concretes. *Construction and building materials*, 17(2), 105-112.
- [7] Toutanji, H. A., & El-Korchi, T. (1995). The influence of silica fume on the compressive strength of cement paste and mortar. *Cement and Concrete Research*, 25(7), 1591-1602.
- [8] Singh T. and Nanda A. K. "Influence of Marble Powder on Mechanical Properties of Mortar and Concrete Mix" NMBCW June 2012
- [9] Aliabdo, A. A., Elmoaty, A. E. M. A., & Auda, E. M. (2014). Re-use of waste marble dust in the production of cement and concrete. *Construction and building materials*, 50, 28-41.
- [10] Aruntaş, H. Y., Gürü, M., Dayı, M., & Tekin, I. (2010). Utilization of waste marble dust as an additive in cement production. *Materials & Design*, 31(8), 4039-4042.
- [11] Pacheco-Torgal, F., & Jalali, S. (2011). Compressive strength and durability properties of ceramic wastes based concrete. *Materials and structures*, 44(1), 155-167.
- [12] IS269:1989 – Specification for ordinary Portland cement, 33 grade
- [13] IS 383:1970 – Specification for coarse and fine aggregates from natural sources for concrete
- [14] IS 2386(Part 1):1963 Methods of test for aggregates for concrete: Part 1 Particle size and shape
- [15] IS: 1199 – methods of sampling and analysis of concrete.
- [16] IS: 516 – methods of test for strength of concrete.