

# Experimental Studies on Fresh Properties of Self-Compacting Geopolymer Concrete using Waste Foundry Sand

Ankit S. Chakraborty<sup>1</sup> Raj L. Shah<sup>2</sup> Prayas B. Variya<sup>3</sup> Prof. Nikunj R. Patel<sup>4</sup>

<sup>1,2,3,4</sup>Department of Civil Engineering

<sup>1,2,3,4</sup>Sardar Patel College of Engineering, Bakrol, Anand, India

**Abstract**— To resolve the problem of carbon emission and to reduce the Labour cost in construction of concrete structures an innovative sustainable concreting technique named “self-compacting geopolymer concrete” is developed. The benefit of using this concreting technique is that the Labour cost reduces due to its self compactability and it also solves the problem of disposal of waste foundry sand. The present investigation is mainly focused on the fresh properties of self-compacting geopolymer concrete with varying molarity of NaOH and using waste foundry sand as replacement of ordinary sand to make this a low-cost concreting technique. Test were performed such as slump flow, T50cm, V-funnel and L-box were conducted to assess the fresh properties. Studies reveals that increasing the molarity of NaOH decreases the fresh properties but increased the compressive strength of SCGC.

**Key words:** SCGC, Self-Compacting Geopolymer Concrete

## I. INTRODUCTION

Concrete is the primary material in construction industry. It consists of cement, coarse aggregate, fine aggregate, water and other admixtures. Generally Ordinary Portland cement is used in concreting but the production of OPC causes a huge amount of carbon emission and also it uses a huge amount of non-renewable natural resources. The concrete construction practice in use is considered as unsustainable because it consumes a huge quantity of sand, stone and water and 2.5 billion tons of OPC per year.

So, to resolve the problem of emission of greenhouse gases Davidovits developed an innovative concreting technique. Davidovits proposed that an alkaline liquid could be used to react with the silicon (Si) and Aluminum (Al) in a source material of geological origin or in by-products materials such as Fly Ash (FA) and Rice Husk (RHA) to produce binders [1]. The two main constituents of geopolymer, namely the source materials and the alkaline liquids [1]. This could be natural mineral such as kaolinite, clays etc. Alternatively, by-products such as fly ash, silica fume, slag, rice husk, GGBS, red mud etc.[1]. The material used as geo-polymer binders should be rich in silicon (Si) and Aluminium (Al). Both Fly Ash and GGBS in certain proportion were found to be geopolymer source materials to obtain sufficient strengths of geopolymer concrete [2]. Alkaline liquids are from soluble alkali metals that are usually sodium or potassium based [1]. The most common alkaline liquid used in geopolymerisation is a combination of sodium hydroxide (NaOH) or Potassium Hydroxide (KOH) and Sodium Silicate or potassium silicate. Many of the GPC mixes earlier tested required the use of high temperature curing. Heat curing substantially assists the chemical reaction that occurs in the geo-polymer paste [1]. Both curing time and curing temperature influence the compressive strength of geopolymer concrete [1]. However recent studies revealed that GPC mixes can be developed for ambient room

temperature [5]. It was noticed that fresh GPC was highly viscous with low workability and hence, super plasticizer (SP) was found to be used to attain adequate workability [2].

One of the major problem faced in construction industry is the lack of skillful labors for concreting but to resolve this problem Japanese scientists Okamura et al and Ozawa et al proposed a new concreting technique named “self-compacting concrete” in which the concrete compacts due to its self-weight and can pass through congested reinforcement easily. Self-compacting concrete has the follow properties: higher slump flow, high viscosity, passing ability and resistance to segregation [3]. Use of self-compacting geopolymer concrete in construction industry can solve the problem of greenhouse gas emission as well as it reduces the problems faced due to lacking of skillful Labour and using waste foundry sand as replacement of river sand can solve the problems of river mining, solves problems of disposal of waste foundry sand and reduces the cost of concreting. Studies reveals that the compressive strength of SCGC increases when thermal cured at 60-70 °C, but it decreases when temperature exceeds 70 °C [7]. It is found that on increasing molarity of NaOH the fresh properties of concrete decreases [6]. It is observed that the alkaline solution, super plasticizer and extra water should be premixed before adding to the dry mix of concrete to get improved workability of SCGC[2-19]. In metal industries for various process in metal casting foundry sand is used. After the casting of metal the burnt fine grained foundry sand can be re-used for various purposes in construction industry. It will reduce the cost of construction. But split tensile strength decreases on increasing the percentage of waste foundry sand. [4].

In the present research we examined how self-compacting geopolymer concrete using waste foundry sand as replacement is good over conventional concrete. Its Fresh properties by conducting tests such as slump flow, T50cm, V-funnel and L-box as per EFNARC [10].

## II. EXPERIMENTAL STUDIES

### A. Materials Used

The materials used in this study were

#### 1) Class F Fly Ash

Nowadays fly ash is the material which is most extensively used in construction industry as a partial replacement of cement. The burning of harder, older anthracite and bituminous coal typically produces Class F fly ash. This fly ash is pozzolanic in nature, and contains less than 7% lime (CaO). Possessing pozzolanic properties, the glassy silica and alumina of Class F fly ash requires a cementing agent, such as Portland cement, quicklime, or hydrated lime mixed with water to react and produce cementitious compounds. Alternatively, adding a chemical activator such as sodium silicate (water glass) to a Class F ash can form a geopolymer.

We are using class F fly ash obtained from “Wanakbori Thermal Power Station, Gujarat, India”.

2) *Ground Granulated Blast Furnace Slag*

It is obtained as a by-product of iron and steel-making from a blast furnace in water or steam, to produce a glassy, granular product that is then dried and ground into a fine powder. It is used as a partial replacement of cement, when it is used in certain proportion with fly ash it significantly helps in increasing the compressive strength. The main components of blast furnace slag are CaO (30-50%), SiO<sub>2</sub> (28-38%), Al<sub>2</sub>O<sub>3</sub> (8-24%), and MgO (1-18%). In general, increasing the CaO content of the slag results in raised slag plasticity and an increase in compressive strength.

3) *River Sand*

Aggregate contains almost 75-80% of the concrete volume. While in SCGC for self compaction the fine aggregate content should be 40% of the mortar volume. Ordinary sand which pass through 4.75mm IS sieve and having no more than 5% coarser material are included in fine aggregate. River sand is obtained by river mining which is a non-renewable source. fine aggregate fills the voids and increases the workability of concrete.

4) *Waste Foundry Sand*

Mostly metal industries prefer sand casting system. In this system mould made of uniform size and uniform sand with high silica content is used. After the casting of metal foundries reuse and recycle the sand but after several times of using it the sand is discarded and it is called waste foundry sand. Its use in construction industry is economical and also solve the problems of its disposal.

5) *Coarse Aggregate*

The aggregate having size more than 4.75mm is termed as coarse aggregate. In order to achieve self compactability and passability of concrete through congested reinforcement coarse aggregate of two different sizes are used in SCGC. In SCGC the coarse aggregate content is 50% of the solid volume and coarse aggregate in two different size at 60:40 ratio can be used.

6) *Super Plasticizer*

Self-compacting concrete can be prepared by compounding admixture with high efficiency water reducing agent. According to requirement of performance of SCGC, climate conditions and the construction technology, combined with concrete raw materials performance, adaptability to cement and mix proportion and other factors, the species and dosage of admixture can be determined through the test.

7) *Alkaline Solution*

Generally, sodium hydroxide or potassium hydroxide and sodium or potassium silicate is used as alkaline activators for formation of C-S-H gel. Studies reveal that only using sodium hydroxide or sodium silicate is not much effective. So, combination of sodium hydroxide and sodium silicate is used generally. Sodium hydroxide pellets is 97-8% purity is generally used and sodium silicate with Na<sub>2</sub>O = 13.7%, SiO<sub>2</sub> = 29.4% and water = 55.9% is generally used. With the increase in concentration of solution in terms of molarity (M) the concrete becomes brittle with increased compressive strength. Cost of sodium hydroxide solids is high and preparation is very caustic. Generally, sodium silicate-to-sodium hydroxide ratio of 2 to 2.5 is maintained in concrete casting which will help in gaining the strength after 24h of casting.

8) *Water*

Water plays an important role in concrete while in self-compacting geopolymer concrete water does not play any important role in gaining strength rather it helps in improving the workability. As studies reveals that geopolymer mix is less workable so to attain self-compact ability extra water is needed to add in the mix.

III. SCOPE OF RESEARCH

In this study we used Class F Fly Ash and Ground Granulated Blast Furnace Slag (GGBFS) in ratio of 70:30 as binder materials. In the first study we conducted fresh property test with 0% replacement of river sand and then we have conducted fresh property test by replacing river sand with waste foundry sand in an amount of 30%, 60% and 100%. We used Coarse Aggregate passing through 12.5 mm sieve and retaining on 10mm sieve. We have used sodium silicate (40% solids) and sodium hydroxide (97-98% purity) as alkaline solution in ratio of sodium silicate-to- sodium hydroxide is 2.5. To attain higher workability we used masterglenium SKY8630 as super plasticizer which is a blended version of Super Plasticizer (SP) and Viscosity Modifying Agent (VMA). Alkaline solution is prepared 24 hours before the practical to be performed. A specified amount of extra water (other than water used in preparation of alkaline solution) is added to attain higher workability because geopolymer mix is having less workability (dry mix). The chemical compositions of materials and mix designation table are as shown below.

Particulars	Class F Fly Ash	Ground Granulated Blast Furnace Slag
Chemical Compositions	High Fe	
% Silica(SiO <sub>2</sub> )	47	30.61
% Alumina(Al <sub>2</sub> O <sub>3</sub> )	23	16.24
% Iron Oxide(Fe <sub>2</sub> O <sub>3</sub> )	15	0.584
% Lime (CaO)	2.3	34.48
% Magnesia(MgO)	0.8	6.79
% TitaniumOxide(TiO <sub>2</sub> )	1	-
% Sulphur Oxide(SO <sub>3</sub> )	0.5	1.85
Loss on Ignition	0.37	2.1
Physical Compositions		
Specific Gravity	2.11	2.9
Fineness(m <sup>2</sup> /kg)	330	400

Table 1: Chemical Compositions of Fly Ash and GGBFS

Chemical Admixture	Relative Density	pH	Chloride Content (%)	Main Component
SKY8630	1.08	≥ 6	<0.2%	Polycarboxylate Ether

Table 2: Properties of Admixtures

Constituent	Value (%)
Silica(SiO <sub>2</sub> )	87.91
Alumina(Al <sub>2</sub> O <sub>3</sub> )	4.7
Iron Oxide(Fe <sub>2</sub> O <sub>3</sub> )	0.94
Lime (CaO)	0.14
Magnesia (MgO)	0.3
Sulphur Oxide (Na <sub>2</sub> O)	0.19
Potassium Oxide (K <sub>2</sub> O)	0.25

Table 3: Chemical Composition of Waste Foundry Sand

IV. MIX PROPORTIONS

Mix	AS/B	Binder	CA	FA	WFS
M1	0.45	450	712	984	0
M2	0.45	450	712	689	295
M3	0.45	450	712	394	590
M4	0.45	450	712	0	984

Table 4: Mix Designations-1

Mix	NaOH	Na <sub>2</sub> SiO <sub>3</sub>	Extra Water (%)	SP (%)	W/B
M1	58	145	20	3	0.4
M2	58	145	20	3	0.4
M3	58	145	20	3	0.4
M4	58	145	20	3	0.4

Table 5: Mix Designations-2

V. MIXING, TESTING, CASTING AND CURING

Mix is prepared in two stages. In first stage coarse aggregate, fine aggregate, fly ash and ground granulated blast furnace slag are dry mixed for 3-4 minutes. In the second stage the alkaline solution, super plasticizer and water is mixed properly and then mixed with the dry mixed materials for 3 minutes. To ensure homogeneity of concrete the materials are allowed to mix for 2-3 minutes more. To access the fresh properties of self-compacting geo-polymer concrete test such slump flow, T<sub>50cm</sub>, V funnel and L-box were conducted as mentioned by EFNARC. The fresh concrete mixtures are then filled into cubes of 150mm x 150mm x 150mm and cylinders of 150mm diameter and 300mm height.




Fig. 1: Comparison of T-50sec with 10M




Fig. 2 Comparison of Slump Flow with 10M




Fig. 3: Comparison of V-Funnel with 10M




Fig. 4: Comparison of L-Box Test with 10M

VI. RESULT

This section discusses the effect on fresh properties of self-compacting geo-polymer concrete due to replacement of sand by certain amount with waste foundry sand.

Mix No.	Description	Slump Flow (mm)	T <sub>50cm</sub>	L-box H <sub>2</sub> /H <sub>1</sub>	V funnel (seconds)
M1	0% replacement	750mm	3	0.9	9.3
M2	30% replacement	670mm	4.5	0.83	12
M3	60% replacement	450mm	Fail	Fail	Fail
M4	100% replacement	Fail	Fail	Fail	Fail

Table 6: Result

As recommended by EFNARC [10] for self-compacting concrete				
	Slump Flow	T <sub>50cm</sub>	L- box	V- funnel
Minimum	650mm	2	0.8	9
Maximum	800mm	5	1	15

Table 7: Result

VII. CONCLUSION

On using Fly Ash and GGBFS as binder material for self-compacting geo polymer concrete can help in reducing CO<sub>2</sub> emission from concrete structures.

- On replacing river sand with waste foundry sand by certain amount can solve the problems of river mining and reduce the cost of concreting.
- On replacing sand up to 30% with ordinary sand give quite good self-compacting properties such as flow ability, pass ability, segregation resistance-stability and viscosity.
- While replacing 60% ordinary sand with waste foundry sand the self-compactability of the concrete decreases and test for self-compacting concrete fails in attaining the values recommended by EFNARC and at 100% replacement the concrete does not show flow ability, pass ability, segregation resistance and viscosity hence fails every criteria for self-compacting concrete by EFNARC.
- This will reduce the labour cost in concreting due to its self-compacting properties.
- The mix designed with aggregate size ranging from 10-16mm gives better fresh properties.

- Problems of disposal of Fly Ash and Ground Granulated Blast Furnace Slag is resolved.
- This type of concreting useful for casting precast concrete members.

#### REFERENCES

- [1] N A Lloyd, B V Rangan, "Geopolymer concrete with fly ash", A Review of Development and Opportunities, 2010.
- [2] C. Sashidhar, J. Guru Jawahar, C. Neelima and D. Pavan Kumar, "Preliminary Studies on self-compacting geopolymer concrete using manufactured sand", Asian Journal Of Civil Engineering(BHRC) VOL. 17, NO. 3, Pg. No. 277-288, 2016.
- [3] Ruza Okrajnov-Bajic, Dejan Vasovic, "Self- compacting concrete and its application in contemporary architectural practice", SPATIUM International Review , No. 20 , pg. no. 28-34 , September 2009.
- [4] Pathariya Saraswati C., Rana Jaykrushna K, Shah Palas A, Mehta Jay G, Assistant Prof. Patel Ankit N., "Application of Waste Foundry Sand for Evolution of Low-Cost Concrete", International Journal of Engineering Trends and Technology, Vol.4 Issue 10, pg. no. 4281-4286, Oct 2013.
- [5] Rajamane NP, Nataraja MC, Lakshmanan N, Ambily PS. Geopolymer concrete - An ecofriendly concrete, The Masterbuilder, vol. 11,2009.
- [6] Memon FA, Nuruddin MF, Khan S, Shafiq N, Ayub T., "Effect of sodium hydroxide solution and compressive strength of self-compacting geopolymer concrete", Journal of Engineering Science and Technology, pg. no. 44-56 , 2013 .
- [7] Memon FA, Nuruddin MF, Samuel D, Shafiq N., Effect of curing conditions on strength of fly ash based self-compacting geo-polymer concrete, International Journal of Civil and Environmental Engineering, vol.3,2011
- [8] Apoorva S., Namrata F. Dabali, "Investigation on strength characteristics of Geopolymer Concrete at Ambient and Oven Curing", International Journal of Scientific and Research Publications, vol6 issue 1, pg. no. 22-24, January 2016.
- [9] Payal Painuly, Itika Uniyal, "Literature Review on Self-Compacting Concrete", International Journal of Technical Research and Applications, vol. 4, issue 2, pg. no. 178-180, (March- April) 2016.
- [10] Specification and guidelines for self-compacting concrete by EFNARC, February 2002.