

# Evaluation of Cost Effective Material for Maintenance of Flexible Pavement

Mr. Vikram. D. Deshmukh<sup>1</sup> Prof. G. N. Kanade<sup>2</sup>

<sup>1,2</sup>TKIET, Warananagar, India

**Abstract**— Roads represent an important infrastructure facility in all countries. Two important parameters for good pavements are pavement design and materials. A good design of bituminous mix is expected to result in a mix which is adequately strong, durable and at the same time environment friendly and economical in order to maintain the pavement. This work is undertaken to prepare cost effective material for maintenance of flexible pavement, by using industrial wastes such as steel slag and foundry sand as a replacement material for fine aggregate in bituminous mix and ground granulated blast furnace slag as a replacement material for fillers in bituminous mix. Fillers play an important role in engineering properties of bituminous paving mixes. Conventionally stone dust, cement and lime are used as filler play an important role in engineering properties of bituminous paving mixes. Conventionally stone dust, cement and lime are used as fillers. Now-a-days disposal of different wastes produced from different Industries is a great problem. These materials pose environmental pollution in the nearby locality because many of them are non-biodegradable. In recent years, applications of industrial wastes have been considered in road construction with great interest in many industrialized and developing countries. The use of these materials in road making is based on technical, economic, and ecological criteria. India has a large network of industries located in different parts of the country and many more are planned for the near future. Several million metric tons industrial wastes are produced in these establishments. If these materials can be suitably utilised in highway construction, the pollution and disposal problems may be partly reduced. Keeping in mind the need for bulk use of these solid wastes in India, it was thought expedient to test these materials and to develop specifications to enhance the use of these industrial wastes in road making, in which higher economic returns may be possible. The possible use of these materials should be developed for construction of low-volume roads in different parts of our country.

**Key words:** Industrial Wastes, Steel Slag, Ground Granulated Blast Furnace Slag, Foundry Sand

## I. INTRODUCTION

Now-a-days disposal of different wastes produced from different Industries is a great problem. These materials pose environmental pollution in the nearby locality because many of them are non-biodegradable. In recent years, applications of industrial wastes have been considered in road construction with great interest in many industrialized and developing countries. The use of these materials in road making is based on technical, economic, and ecological criteria. The lack of traditional road materials and the protection of the environment make it imperative to investigate the possible use of these materials carefully. India has a large network of industries located in different parts of the country and many more are planned for the near future. Several million metric tons industrial wastes are produced in

these establishments. Traditionally soil, stone aggregates, sand, bitumen, cement etc. are used for road construction. Natural materials being exhaustible in nature, its quantity is declining. Also, cost of extracting good quality of natural material is increasing. Concerned about this, the scientists are looking for alternative materials for highway construction, and industrial wastes product is one such category. If these materials can be suitably utilized in highway construction, the pollution and disposal problems may be partly reduced. Roads are very important national investment and require maintenance to keep them in a satisfactory condition and ensure safe passage at an appropriate speed and with low road user cost. Late or insufficient maintenance will increase the ultimate repair costs, inconvenience and reduce safety. Pavement maintenance is therefore an essential function and should be carried out on timely basis. From the budget allocation plan of India the amount for maintenance and repair of highways is RS.1089.49 crores in 2011-12 and RS. 1272.49 in 2012-13 for length of 33,20,596 km. Hence amount of maintenance per km in 2011-12 is RS. 3281 and for year 2012-13 is RS. 3832. So it is necessary to develop cost effective material for maintenance of flexible pavements.

Generally a bituminous mixture is a mixture of coarse aggregates, fine aggregate, filler and binder. Two things are of major considerations in flexible pavement engineering, mix design and the pavement design. A good design of bituminous mix is expected to result in a mix which is adequately (i) Strong (ii) Durable (iii) Resistive to fatigue and permanent deformation (iv) Environment friendly (v) Economical. A mix designer tries to achieve these requirements through a number of tests on the mix with varied proportions and finalizes with the best one.

### A. Objective of Bituminous Mix Design:

Bituminous mix consists of a mixture of aggregate continuously graded from maximum size, typically less than 25 mm, fine filler that is smaller than 0.075 mm. Sufficient bitumen is added to the mix so that the compacted mix will have acceptable elastic properties. The main objectives of bituminous mix design aims to determine the proportion of bitumen, filler, fine aggregate, and coarse aggregate to produce a mix which is workable, strong, durable and economical. The objective of the mix design is to produce a bituminous mix by proportioning various components so as to have-

- 1) Sufficient strength to resist shear deformation under traffic at varying temperature.
- 2) Sufficient air voids in the compacted bitumen to allow for additional compaction by traffic.
- 3) Sufficient durability.
- 4) Should be economical.
- 5) Adequate coefficient of friction to prevent skidding of vehicle.
- 6) Dust proof surface so that traffic safety is not impaired by reducing visibility.

## II. INTRODUCTION TO FLEXIBLE PAVEMENT MAINTENANCE

### A. Meaning of Flexible Pavements:

Flexible pavements are constructed of several layers of natural granular material covered with one or more water-proof bituminous surface layers, and as the name imply, are considered to be flexible. A flexible pavement will flex (bend) under the load of a tyre. In flexible pavements, the load distribution pattern changes from one layer to another, because the strength of each layer is different. The strongest material (least flexible) is in the top layer and the weakest material (most flexible) is in the lowest layer.

The wheel load acting on the pavement will be distributed to a wider area, and the stress decreases with the depth. Taking advantage of this stress distribution characteristic, flexible pavement normally has many layers. Hence, the design of flexible pavement uses the concept of layered system. Based on this, flexible pavement may be constructed in a number of layers and the top layer has to be of best quality to sustain maximum compressive stress, in addition to wear and tear. The lower layers will experience lesser magnitude of stress and low quality material can be used. Flexible pavements are constructed using bituminous materials. These can be either in the form of surface treatments (such as bituminous surface treatments generally found on low volume roads) or, asphalt concrete surface courses (generally used on high volume roads such as national highways). Flexible pavement layers reflect the deformation of the lower layers on to the surface layer (e.g., if there is any undulation in sub-grade then it will be transferred to the surface layer). In the case of flexible pavement, the design is based on overall performance of flexible pavement, and the stresses produced should be kept well below the allowable stresses of each pavement layer.

### B. Pavement Deterioration and its types:

Pavement deterioration is the process by which distress (defects) develop in the pavement under the combined effects of traffic loading and environmental conditions. Distresses in flexible pavement are as follows:

- 1) Fatigue (Alligator) Cracking
- 2) Polished Aggregate
- 3) Bleeding
- 4) Potholes
- 5) Block Cracking
- 6) Raveling
- 7) Corrugation and shoving
- 8) Rutting
- 9) Depression
- 10) Stripping
- 11) Longitudinal cracking
- 12) Transverse cracking
- 13) Patching
- 14) Polished aggregates
- 15) Water bleeding and pumping

### C. Main Causes of Distresses In Pavement:

- 1) Traffic
- 2) Environmental condition
- 3) Method of construction and quality of construction material

### 4) Moisture infiltration.

Pavements fail prematurely because of many factors, there are four primary reasons pavements fail prematurely:

- 1) Failure in design
- 2) Failure in construction
- 3) Failure in material
- 4) Failure in maintenance

### D. Conventional Material used for Maintenance of Flexible Pavement:

#### 1) Slurry Seal Coat:

Slurry seal consists of a mixture of sand, Portland cement, water and emulsified asphalt mixed to a rich consistency. It is spread in a thin layer over the pavement. Portland cement is added for stabilizing and setting the slurry. Slurry seal coats are normally used to fill cracks and minor depressions in older AC pavement.

#### 2) Emulsified asphalt:

Emulsified asphalt is a mixture of asphalt cement and water. This asphalt/water ratio is about 60/40. The bitumen content in the emulsion is around 60% and the remaining is water. Sometimes a special type of emulsified asphalt is specified in the Special Provisions. The special type of emulsified asphalt is 50/50 mixture of water and emulsified asphalt. An asphalt emulsion consists of three basic ingredients: asphalt, water, and an emulsifying agent.

#### 3) Final seal (Rubber Crumb Slurry):

A slurry seal, using rubber crumbs instead of aggregate can be used to fill the wider active cracks. Hand tools are used to mix and apply this slurry seal.

The slurry consisted of the following mix by volume:

- Rubber crumbs 60%
- Stable grade bitumen emulsion 35%
- Cement 5%.

#### 4) Micro Surfacing:

Micro surfacing is a mix of polymer-modified emulsion, well-graded crushed mineral aggregate, mineral filler (normally Portland cement), water, and chemical additives. The aggregate, mineral filler, emulsion, and water are mixed in a truck-mounted travelling plant, which is deposited into a spreader box. No compaction is needed, traffic may be allowed over the application within an hour after placement.

#### 5) Pothole Repair Material:

The four components of a typical mix are:

- Coarse aggregate (retained on 4.75mm sieve)
- Fine aggregate (passing 4.75mm sieve but retained on 75 $\mu$ )
- Filler (passing 75 $\mu$ ), may be cement.
- Binder: Bitumen etc.

#### 6) Stone Mastic Asphalt (SMA) Mortar:

Mixture of asphalt cement (and any additives), filler (all material passing through 75  $\mu$  sieve) and fibres blended by volume. stone flux. Quenching process of molten slag by water is converting it into a fine, granulated slag of whitish colour.

#### 7) Foundry Sand:

Sand is used in the foundry industry mainly for making moulds for the casting. This sand is generally recycled. After a repeated use, they lose their characteristics and thereby becoming unsuitable for further use in manufacturing

process. This sand is usually discarded and dumped in the landfill as a waste.

8) *Course Aggregate:*

The mineral aggregates most widely used in bitumen mixes are crushed stone, crushed or uncrushed gravel. Since mineral aggregate constitutes of approximately 80% to 96% by weight and approximately 80% by volume of the total mix. Their influence upon the final characteristics of bituminous mixes is very great.

9) *Fine Aggregate:*

It shall be fraction passing 4.75 mm and retained on 75  $\mu$  sieve consisting of crushed stone or natural sand. Its function is to fill up the voids of the coarse aggregate. Here in this work natural sand is used as fine aggregate. It should be clean, hard, strong, free of organic impurities and free of silt and clay.

10) *Filler:*

It is the filler material used in bituminous mix which passes through 75  $\mu$  sieve. The fillers should be inert material. The filler should be fresh, have uniform consistency and free of foreign matter.

11) *Bitumen:*

Bitumen is the residue or by-product when the crude petroleum is refined. Bitumen is act as a binder in bituminous mix. Different grade of bitumen are used in different mix. Here we used 30/40 bitumen for preparation of bituminous mix.

### III. EXPERIMENTAL STUDY

A. *Material Used:*

1) *Steel Slag:*

Steel slag, a by-product of steel making, is produced during the separation of the molten steel from impurities in steel-making furnaces.

2) *Ground Granulated Blast Furnace Slag:*

Blast Furnace Slag is a byproduct obtained in the manufacturing of Pig iron in the Blast furnace and is formed by the combination of earthy constituents of iron ore with lime

B. *Test Results:*

a) *Coarse Aggregate:*

- 1) Water Absorption= 1.4985%
- 2) Specific Gravity= 2.90
- 3) Fineness modulus = 2.43
- 4) loss Angelis=15.25%
- 5) Impact value=5.28%

b) *Fine Aggregate:*

- 1) Water Absorption= 1.69%
- 2) Specific Gravity= 2.85
- 3) Fineness modulus = 5.66

c) *Cement:*

- 1) Fineness Test = 7%
- 2) Specific gravity= 3.15

d) *Steel slag:*

- 1) Water Absorption= 0.95%
- 2) Specific Gravity= 2.69
- 3) Fineness modulus = 4.545

e) *Foundry sand:*

- 1) Specific Gravity= 2.59
- 2) Fineness modulus =2.21

f) *Ground granulated blast furnace slag:*

- 1) Specific Gravity= 2.17
- 2) Fineness test=2.08%

### IV. TESTING OF BITUMINOUS MIX AND RESULTS

A. *Brief Procedure of Marshall Test:*

- 1) 1200 gm aggregate are weighted and heated up to 154-160 degree C.
- 2) Bitumen is heated upto 175 -190 degree C.
- 3) Aggregate & Bitumen are mixed thoroughly until a uniform grey colour is obtained.
- 4) Marshall Mould diameter 100 mm & 64 mm height compacted with 75 blows on each face.
- 5) Mould is taken out kept under normal laboratory temp for 12 hours.
- 6) It is immersed in water bath kept at a constant temp. 60 degrees for 30 minutes.
- 7) Load is applied vertically at the rate of 50mm per minute.
- 8) The maximum load at sample fails is recorded as the Marshall Stability value.
- 9) Corresponding vertical strain is termed as the flow value.

B. *Test Procedure:*

A specimen from the Water bath is removed and placed in the lower segment of the testing head. The upper segment of the testing head on the specimen is placed, and the complete assembly is placed in position in the loading machine. The dial gauge is placed in position over one of the guide rods. Readings of dial gauge and proving ring are recorded.

C. *Parameters used:*

1) *Theoretical Maximum Specific Gravity of Mix:*

$$G_t = 100 / (W_1/G_1 + W_2/G_2 + W_3/G_3 + W_4/G_4)$$

Where,

W<sub>1</sub> = Percentage by weight of coarse aggregate in total mix

W<sub>2</sub> = Percentage by weight of fine aggregate in total mix

W<sub>3</sub> = Percentage by weight of filler in total mix

W<sub>4</sub> = Percentage by weight of bitumen in total mix

G<sub>1</sub> = Specific gravity of coarse aggregate

G<sub>2</sub> = Specific gravity of fine aggregate

G<sub>3</sub> = Specific gravity of filler

G<sub>4</sub> = Specific gravity of bitumen.

2) *Bulk Density of mix:*

$$G_m = \text{weight in Air} / (\text{weight in air} - \text{weight in water}) * 1 \text{ gm/cm}^3$$

3) *Volume of Air Voids:*

$$V_v = ((G_t - G_m) / G_t) * 100$$

4) *Void in Mineral Aggregate (VMA):*

$$VMA = V_v + V_b$$

Where,

V<sub>v</sub> = Volume of air voids, V<sub>b</sub> = Volume of bitumen.

5) *Void Filled With Bitumen (VFB):*

$$V_b = G_m * (W_4/G_4)$$

Where,

G<sub>m</sub> = Bulk Density

W<sub>4</sub> = Percent by weight of bitumen in total mix.

G<sub>4</sub> = Specific gravity of bitumen.

**D. Marshall Test Results:**

The results of the Marshall test of samples and average Marshall Properties of Samples prepared with conventional mix for varying bitumen contents have been presented below:

Bitumen %	Sample No.	Wt in Air (gm)	Wt in water (gm)	Flow Value (mm)	Stability Value (kg)	Corrected Stability value	G <sub>t</sub>	Unit Wt (g/cc) G <sub>mm</sub>	% Air Voids (V <sub>v</sub> )	VMA (%)	V <sub>b</sub> (%)	VFB (%)
6%	1	1232	748	6	410	446.9	2.62	2.54	3.05	18.13	15.08	83.17
6%	2	1103	669	7	415	518.75	2.62	2.54	3.05	18.13	15.08	83.17
6%	3	1129	656	7	425	425	2.62	2.38	9.16	23.29	14.13	60.66
6.25%	1	1180	699	6	419	477.66	2.61	2.45	6.13	21.29	15.16	71.20
6.25%	2	1182	689	9	430	490.2	2.61	2.39	8.429	23.22	14.79	63.7
6.25%	3	1179	715	7	421	558.89	2.61	2.54	2.681	18.40	15.72	85.43
6.5%	1	1177	689	5	490	612.5	2.59	2.41	6.94	22.44	15.50	69.67
6.5%	2	1182	697	7	503	573.42	2.59	2.43	6.17	21.8	15.63	71.69
6.5%	3	1178	700	4	480	547.2	2.59	2.46	5.01	20.84	15.83	75.95
6.75%	1	1225	741	5	415	493.85	2.63	2.53	3.80	20.7	16.90	81.64
6.75%	2	1105	610	8	431	491.34	2.63	2.23	15.2	30.1	14.9	49.50
6.75%	3	1133	653	7	419	523.75	2.63	2.36	10.26	26.03	15.77	60.58
7%	1	1184	704	9	407	463.98	2.57	2.46	4.28	21.32	17.04	79.92
7%	2	1181	701	8	416	495.04	2.57	2.46	4.28	21.32	17.04	79.92
7%	3	1179	686	6	384	437.76	2.57	2.39	7	23.56	16.5	70.28

Table 4.1: Results of Marshall Test for Conventional Mix

From the test results optimum binder content selected as 6.5%

Bitumen (%)	Sample No.	Wt in Air (gm)	Wt in water (gm)	Flow Value (mm)	Stability Value (kg)	Corrected Stability value	G <sub>t</sub>	Unit Wt (g/cc) G <sub>mm</sub>	% Air Voids (V <sub>v</sub> )	VMA (%)	V <sub>b</sub> (%)	VFB (%)
6.5%	1	1161	695	4	500	570	2.54	2.49	1.97	17.99	16.024	89.072
6.5%	2	1212	720	4	480	571.20	2.54	2.46	3.15	18.98	15.83	83.404
6.5%	3	1181	700	5	482	525.38	2.54	2.46	3.15	18.98	15.83	83.404

Table 4.2: Results of Marshall test for 50 % replacement of fine aggregates and filler material (steel slag as a fine aggregates and GGBFS as a filler material).

Bitumen (%)	Sample No.	Wt in Air (gm)	Wt in water (gm)	Flow Value (mm)	Stability Value (kg)	Corrected Stability	G <sub>t</sub>	Unit Wt (g/cc) G <sub>mm</sub>	% Air Voids (V <sub>v</sub> )	VMA (%)	V <sub>b</sub> (%)	VFB (%)
6.5	1	1198	706	4	495	589.05	2.49	2.43	2.41	18.04	15.63	86.265
6.5	2	1178	672	5	492	560.8	2.49	2.32	6.82	21.76	14.93	70.54
6.5	3	1193	692	5	492	560.8	2.49	2.38	4.418	19.735	15.31	77.61

Table 4.3: Results of Marshall test for 60 % replacement of fine aggregates and filler material (steel slag as a fine aggregates and GGBFS as a filler material).

Bitumen (%)	Sample No.	Wt in Air (gm)	Wt in water (gm)	Flow Value (mm)	Stability Value (Kg)	Corrected stability Kg	G <sub>t</sub>	Unit Wt (g/cc) G <sub>mm</sub>	% Air Voids (V <sub>v</sub> )	VMA (%)	V <sub>b</sub> (%)	VFB (%)
6.5	1	1182	686	5	490	583.1	2.47	2.38	3.641	18.96	15.31	80.79
6.5	2	1187	671	5	485	552.9	2.47	2.30	6.88	21.68	14.80	68.28
6.5	3	1198	708	6	484	575.96	2.47	2.44	1.23	16.93	15.70	92.74

Table 4.4: Results of Marshall test for 70 % replacement of fine aggregates and filler material (steel slag as a fine aggregates and GGBFS as a filler material).

Bitumen (%)	Sample No:	Wt in Air (gm)	Wt in water (gm)	Flow Value (mm)	Stability Value (kg)	Corrected Stability value	Gt	Unit Wt (g/cc) $G_{mm}$	% Air Voids (Vv)	VMA (%)	Vb (%)	VFB (%)
6.5	1	1172	680	5	480	547.2	2.45	2.38	2.86	18.18	15.32	84.27
	2	1197	690	5	475	541.5	2.45	2.36	3.67	18.86	15.19	80.54
	3	1140	650	6	478	597.5	2.45	2.42	1.22	16.79	15.57	92.73

Table 4.5: Results of Marshall test for 80 % replacement of fine aggregates and filler material (steel slag as a fine aggregates and GGBFS as a filler material).

Bitumen (%)	Sample No:	Wt in Air (gm)	Wt in water (gm)	Flow Value (mm)	Stability Value (kg)	Corrected stability value	Gt	Unit Wt (g/cc) $G_{mm}$	% Air Voids (Vv)	VMA (%)	Vb (%)	VFB (%)
6.5	1	1183	703	4	472	538.08	2.49	2.46	1.2	17.03	15.83	92.95
	2	1182	680	5	470	559.3	2.49	2.35	5.62	20.74	15.12	72.90
	3	1185	711	4	472	538.08	2.49	2.50	0.4	16.49	16.08	97.57

Table 4.6: Results of Marshall test for 50 % replacement of fine aggregates and filler material (foundry sand as a fine aggregates and GGBFS as a filler material).

Bitumen (%)	Sample No:	Wt in Air (gm)	Wt in water (gm)	Flow Value (mm)	Stability Value (kg)	Corrected stability value	Gt	Unit Wt (g/cc) $G_{mm}$	% Air Voids (Vv)	VMA (%)	Vb (%)	VFB (%)
6.5	1	1101	653	5	468	617.76	2.47	2.45	0.81	16.58	15.77	95.11
	2	1169	694	6	465	581.125	2.47	2.46	0.4	16.23	15.83	97.54
	3	1215	700	6	485	577.15	2.47	2.36	4.45	19.64	15.19	77.34

Table 4.7: Results of Marshall test for 60 % replacement of fine aggregates and filler material (foundry sand as a fine aggregates and GGBFS as a filler material).

Bitumen (%)	Sample No:	Wt in Air (gm)	Wt in water (gm)	Flow Value (mm)	Stability Value (kg)	Corrected stability value	Gt	Unit Wt (g/cc) $G_{mm}$	% Air Voids (Vv)	VMA (%)	Vb (%)	VFB (%)
6.5	1	1142	673	6	460	575	2.47	2.43	1.62	17.26	15.63	90.61
	2	1199	706	6	454	494.86	2.47	2.43	1.62	17.26	15.63	90.61
	3	1196	727	6	458	522.12	2.47	2.39	3.24	18.62	15.38	82.60

Table 4.8: Results of Marshall test for 70 % replacement of fine aggregates and filler material (foundry sand as a fine aggregates and GGBFS as a filler material).

Bitumen (%)	Sample No:	Wt in Air (gm)	Wt in water (gm)	Flow Value (mm)	Stability Value (kg)	Corrected stability value	Gt	Unit Wt (g/cc) $G_{mm}$	% Air Voids (Vv)	VMA (%)	Vb (%)	VFB (%)
6.5	1	1172	680	6	450	462.5	2.43	2.39	1.69	17.07	15.38	90.09
	2	1197	690	6	447	390.04	2.43	2.36	2.88	18.06	15.18	84.05
	3	1140	650	6	445	529.55	2.43	2.33	4.12	19.11	14.99	78.44

Table 4.9: Results of Marshall test for 80 % replacement of fine aggregates and filler material (foundry sand as a fine aggregates and GGBFS as a filler material).

E. Interpretation of Results

- 1) From the result of stability vs Bitumen it is learnt that optimum binder content for samples prepared with Normal mix is found to be 6.5 %.
- 2) From the flow value result of different bitumen content, it is observed that the flow value for the bitumen content 6.5 % is 5.33 mm which less as compare to 6 %, 6.25 %, 6.75 % & 7 % bitumen content so optimum bitumen content is 6.5 %.

- 3) The result for Marshall stability with 70 % replacement of fine aggregates using steel slag are more as compared to other trials made using steel slag; the stability values obtained are 583.1 kg, 552.9 kg, and 575.96 kg.
- 4) The result for Marshall stability with 60 % that; replacement of fine aggregates using foundry sand are more as compared to other trials made using foundry sand, the stability values obtained are 617.6 kg, 581.125 kg, and 577.15 kg.
- 5) Therefore optimum percentage of replacement obtained from Marshall Test results for steel slag is 70% and for foundry sand is 60%.

1) *For Conventional Mix:*

Considering for 10 m<sup>2</sup> area

Quantities of aggregates for 10 m<sup>2</sup> area is 0.27 m<sup>3</sup>

54.07 kg bitumen used per m<sup>3</sup> aggregates.

For 0.27 m<sup>3</sup> of aggregates, 14.6 kg bitumen is required.

Volume of aggregates = 0.27 m<sup>3</sup>

1) Coarse aggregates = 0.135 m<sup>3</sup> × 820 = RS. 110.7

2) Fine aggregates = 0.0918 m<sup>3</sup> × 1500 = RS. 137.7

3) Filler = 0.0432 m<sup>3</sup> × 434 = RS. 18.74

Total cost of aggregates (0.27 m<sup>3</sup>) = RS. 267.15

Cost of bitumen (54.07 kg) = 14.6 × 32.763 = RS. 478.30

Total cost of mix = RS. 745.43

It is the cost for normal mix.

From the Marshall Stability result of different mix we conclude that:

60% replacement of fine aggregates by foundry sand and filler by GGBFS gives maximum value of Marshall Stability.

70% replacement of fine aggregates by steel slag and filler by GGBFS gives maximum value of Marshall Stability. So considering these two materials for cost comparison

F. *Cost Comparison for Material*

1) *For Mix with Foundry Sand:*

Volume of aggregates = 0.27 m<sup>3</sup>

1) Coarse aggregates = 0.135 m<sup>3</sup> × 820 = RS. 110.7

2) Fine aggregates = 0.03672 m<sup>3</sup> × 1500 = RS. 55.08

3) Foundry sand = 0.05508 m<sup>3</sup> × 150 = RS. 8.26

4) Filler = 0.01728 m<sup>3</sup> × 434 = RS. 7.50

5) GGBFS = 0.02592 m<sup>3</sup> × 300 = RS. 7.78

Total cost of aggregates = 0.27 m<sup>3</sup> = RS. 189.32

Cost of bitumen = 14.6 × 32.763 = RS. 478.30

Therefore saving in cost for 10 m<sup>2</sup> is RS. 77.81 by using 60 % foundry sand replacement for fine aggregates and filler by GGBFS in bituminous mix. Hence saving in cost per m<sup>3</sup> is RS.7.78.

2) *Cost for Mix with Steel Slag:*

Volume of aggregates = 0.27 m<sup>3</sup>

Coarse aggregates = 0.135 m<sup>3</sup> × 820 = RS. 110.7

Fine aggregates = 0.02754 m<sup>3</sup> × 1500 = RS. 41.31

Steel slag = 0.06426 m<sup>3</sup> × 80 = RS. 5.14

Filler = 0.01296 m<sup>3</sup> × 434 = RS. 5.62

GGBFS = 0.03024 m<sup>3</sup> × 300 = RS. 9.072

Total cost of aggregates (0.27 m<sup>3</sup>) = RS. 171.212

Cost of bitumen = 14.6 × 32.763 = RS. 478.30

Therefore saving in cost for 10 m<sup>2</sup> is RS. 95.91 by using 70 % steel slag replacement for fine aggregates and

filler by GGBFS in bituminous mix. Hence saving in cost per m<sup>3</sup> is RS.9.59.

(All the rates are taken as per DSR 2016-17)

So, from above cost comparison, mix prepared with 70 % replacement of fine aggregates by steel slag and 70 % replacement of filler by GGBFS was found to be most cost effective mix.

V. CONCLUSION

- 1) From the result and analysis of various properties of steel slag and foundry sand it is found that these materials can be used as fine aggregates as replacement for natural sand and ground granulated blast furnace slag can be used as replacement for fillers in bituminous mix.
- 2) Bituminous mixes prepared using conventional mix and different bitumen content gives the optimum bitumen content as 6.5 %.
- 3) Bituminous mixes prepared with 60 % replacement of fine aggregates with foundry sand and 60 % replacement of filler with GGBFS gives the Marshall Stability value as 591.87 kg which is almost 50 kg more as compared to the other mixes with different % of foundry sand and GGBFS.
- 4) Bituminous mixes prepared with 70 % replacement of fine aggregates with steel slag and 70 % replacement of filler with GGBFS gives the Marshall stability value as 570.65 kg which are high as compared to the other trials of steel slag.
- 5) Saving in cost per 1m<sup>2</sup> is Rs.9.59 for bituminous mixes prepared with 70 % replacement of fine aggregates with steel slag and filler by GGBFS.
- 6) Saving in cost per 1m<sup>2</sup> is Rs.7.78 for bituminous mixes prepared with 60% replacement of fine aggregates with Foundry sand and filler by GGBFS.
- 7) By using steel slag and foundry sand in bituminous mix an environment effects from wastes and disposal problems of waste can be reduced.
- 8) By using foundry sand more than 60% replacement for fine aggregates and 60 % replacement of filler with GGBFS gives less result for Marshall stability in next trials.
- 9) By using steel slag more than 70 % replacement for fine aggregates and 70 % replacement of filler with GGBFS gives less result for Marshall stability in next trials.
- 10) So final conclusion is that cost effective material is 70 % replacement of fine sand by steel slag and 70 % replacement of filler by GGBFS.

REFERENCES

- [1] Ann Johnson, (February 2000), "Best Practices Handbook on Asphalt Pavement Maintenance" Minnesota T2/LTAP Program, Center for Transportation Studies, University of Minnesota.
- [2] David P. Orr, (March 2006), "Pavement Maintenance" Cornell Local Roads Program 416 Riley-Robb Hall Ithaca, New York.
- [3] Dr. R Gary Hicks, (June 2000), "Selecting a Preventive Maintenance Treatment for Flexible Pavements", Foundation for Pavement Preservation Washington pp.3-87.

- [4] Dr. S Basak, Dr. A. K. Bhattacharya (April 2010), "A New Horizon in the Field of Maintenance and Effective Upkeepment of Bituminous Road Surface, Global Journal of Researches in Engineering, Vol. 10, pp.79-83.
- [5] FikerAlebachew, (April 2005), "Pavement Distresses on Addis Ababa City Arterial Roads, Causes and Maintenance Options", A Thesis Presented to the School of Graduate Studies Addis Ababa University Faculty of Technology, pp.53-107.
- [6] Found M. Khalaf, (August 2006), "Recycling of Clay Bricks as Aggregate in Asphalt Concrete", School of the Built Environment, Napier University, Edinburgh, EH 10 5 DT Scotland, UK.
- [7] G.D. Airey, A.C. Collop and N.H. Thom, "Mechanical Performance of Asphalt Mixtures Incorporating Slag and Glass Secondary Aggregate", Nottingham Centre for Pavement Engineering, Universal of Nottingham, UK.
- [8] IRC: 82-1982, "Code of Practice for Maintenance of Bituminous Surface of Highways" IRC New Delhi.
- [9] John Emery, "Steel Slag Utilization in Asphalt Mixes", National Slag Association.
- [10] MeenaMurmu, "Evaluation of Strength Characteristic of Steel Slag Hydrated Matrix", A Thesis Submitted In Partial Fulfilment Of The Requirement For The Degree Of Master Of Technology In Civil Engineering.
- [11] Prof. Prithvi Singh Kandhal, (October – December 2008), "A Simple and Effective Method of Repairing Potholes in India", paper no.544 journal of Indian road congress, volume 69-3.
- [12] Robin I. Schoeder (1994), "The Use of Recycled Material in Highway Construction", Public Roads Magazine, Vol-58-No.2.
- [13] Scott Zinke, Brian Hogge, (July 2005), "Evaluation of Pavement Crack Treatments Literature Review" Connecticut Advanced Pavement Laboratory.
- [14] Stephan Q.S.Lee, (November 1999), "Advanced Hot in Place Recycling for Cost Effective Maintenance of asphalt pavements", International seminar on highway rehabilitation and maintenance New Delhi, India.
- [15] Tara Sen and Umesh Mishra, (June 2010), "Usage of Industrial Waste Product in Village Road Construction", International Journal of Environmental Science and Development, Vol.1, No.2 pp(122-126)
- [16] Teoh Cherk Yi, (November 2008), "Performance Evaluation of Steel Slag as Natural Aggregates Replacement in Asphaltic Concrete", Connecticut Advanced Pavement Laboratory.
- [17] Ravindra N Patil, Abhishek M Loya and PreranaPatil (JULY 2015), "Ecofriendly Flexible Pavements Incorporating Waste Product", International Journal of Modern Trends in Engineering and Research (E-ISSN NO: 2349-9745, Dated July 2015).
- [18] ZemichaelBerheMehari, (Feb 2007), " Effect Of Different Types of Filler Materials on Characteristics of Hot-Mix – Asphalt Concrete", A Thesis submitted to School of Graduate Studies of Addis Ababa University In Partial Fulfilment of the Requirements for the Degree of Master of Science In Civil Engineering.
- [19] Zore T.D, S.S. Valunjkar, (2010), "Utilization of Fly Ash and Steel Slag in Road Construction- A Comparative Study" EJGE journal Vol.15.

*Books:*

- [20] Highway Engineering by S.C Rangwala.
- [21] Highway Engineering by S.K Khanna and C.E.G Justo.