

Use of Rice Husk Ash as Partial Replacement with Cement in Concrete

Dipak Muknar¹ Madhav Patil² Devanand Rathod³ Mahesh Narawade⁴ Prof. Prashant Jogdand⁵

⁵Professor

^{1,2,3,4,5}Department of Civil Engineering

^{1,2,3,4,5}G. H. Raisoni College of Engineering and Management, Wagholi, Pune, India

Abstract— The optimized RHA, by controlled burn or grinding, has been used as a pozzolanic material in cement and concrete. Using it provides several advantages, such as improved strength and durability properties, and environmental benefits related to the disposal of waste materials and to reduced carbon dioxide emissions. Up to now, little research has been done to investigate the use of RHA as supplementary material in cement and concrete production. The main objective of this work is to study the suitability of the rice husk ash as a pozzolanic material for cement replacement in concrete. However it is expected that the use of rice husk ash in concrete improve the strength properties of concrete. Also it is an attempt made to develop the concrete using rice husk ash as a source material for partial replacement of cement, which satisfies the structural properties of concrete like compressive strength. From the entire experimental work & studies it is concluded that mix M20 with the replacement of 20% is the best combination among all mixes, which gives the maximum compressive strength.

Keywords: Rice Husk Ash, Agricultural Residues Utilization, Light Weight Structural Concrete, Cost Effective Housing

I. INTRODUCTION

The construction industry relies heavily on conventional materials such as cement, sand and granite for production of concrete. Concrete is the basic civil engineering composite. The quality of concrete is determined by the quality of paste/mix. It is the world's most consumed man made material. Its great versatility and relative economy in filling wide range of needs has made it a competitive building material. The demand for concrete for today's infrastructural development is rising day-by-day. In light of this, the non-availability of natural resources to future generation has also been realized. Concrete production is not only a valuable source of societal development but also a significant source of employment. Following a natural growth in population, the amount and type of waste materials have increased accordingly creating thus environmental problems. Historically agricultural and industrial wastes have created waste management and pollution problems. Different alternative waste materials and industrial by-products such as fly ash, bottom ash, recycled aggregates, crumb rubber, saw dust, brick bats etc. were replaced with natural aggregates. Although these materials are traditionally considered as "primitive" and therefore inferior to more highly processes in terms of safety, durability, performance, occupant's health and comfort with respect to environmental issue, consumption of environmental products and energy within the construction industry has created a significant demand for raw materials and for production thereby contributing to the many environmental problems associated with diverse ecosystem. The wastes have generally no commercial value and are locally available at a minimal transportation cost. The

use of these wastes has complemented other traditional materials in construction and hence provides practical and economic advantages. Also proper utilization of these wastes conserves the natural resources and protects the environment. Apart from the above mentioned waste materials, the rice husk can also be used in concrete due to the following points:- (i) Large scale production of rice in the coastal states of India and in the other countries of Asia. (ii) It is the staple food in majority of the countries of the world and thus generates the husk in Mega-tonnes per year. (iii) After the rice grain is collected, the husk or the ash is thrown away here and there causing environmental pollution (iv) Some percentage of husk serves as eatables for the domestic animals, while majority are being wasted. (v) Little part of it when mixed with cow dung and other organic wastes serves as good manure to the plants (vi) Helpful in cost effective housing and low rise buildings. (vii) Serves as an environment-friendly construction material. With the quest for affordable housing system for both the rural and urban population of India and other developing countries, various proposals focusing on cutting down conventional building material costs have been put forward. Finding a substitute for the aggregate used today is a task that is worth studying because it helps in preserving conventional materials for future

II. REVIEW OF LITERATURES

The literatures regarding the potential uses of rice husk as one of the suitable aggregates for concrete have been reviewed and are presented below. Mehta and Pirth (2000) investigated the use of RHA (Rice Husk Ash) to reduce temperature in high strength mass concrete and concluded that RHA is very effective in reducing temperature of mass concrete compared to OPC concrete. RHA which is an agricultural by-product has been reported to be a good pozzolanic material by numerous researchers. RHA is obtained after burning of rice husk at a very high temperature.

Malhotra and Mehta (2004) reported that ground RHA with fine particle size than OPC improves concrete properties, including higher substitution amounts in lower water absorption values and the addition of RHA caused an increment in the compressive strength. Adewuyi and Ola (2005) have carried out research on the binary blends of OPC with different pozzolanic material in making cement composites. Supplementary cementitious materials have been proven to be effective in meeting most of the requirements of durable concrete. Habeeb and Fayyadh (2009) have investigated the influence of RHA average particle size on properties of concrete and found out that at early ages the strength was comparable, while at the age of 28 days, the finer RHA exhibited higher strength than the sample with coarser RHA. Lee et al (2005) in their study concluded that some of the waste products like Rice husk which possess pozzolanic properties and used in the blended cements include fly ash, silica fume, volcanic ash, corn cob ash hence providing good

strength properties to concrete. Gunduz and Ugur (2004) in their study concluded that the greatest advantages of light weight concrete are its low density, allowing for construction on the ground with only moderate bearing capacity, the use of less reinforcement, the ability to construct taller structures, greater economy in lifting and use of more thermally efficient material. The unit weight of rice husk concrete can be lowered by either using porous materials, therefore lightweight aggregates instead of ordinary ones, introducing air into mortar or removing the fine fraction of aggregate and then by partially compacting the concrete. In all cases, the main goal is to introduce voids into aggregates and mortar or between mortar or aggregate. Khedari et al (2001) have studied the characteristic properties of various light weight aggregates like pumice, coal slag, flying ash, rice husk, straw, saw dust, cork granules, wheat husk, coconut fiber and coconut shell used in partial replacement for concrete production. The organic waste used in light weight concrete is mainly of plant origin. They concluded that by using plant waste that is abundantly found in rural areas, it may be possible to construct cheaper and good quality agricultural constructions. Sari and Pasamehmetoglu (2004) have concluded that rice husk as an organic waste, is a significant problem in rice cultivating areas because it is not used profitably and is generally burned after harvest, which causes environmental problems. Generally concrete with a unit weight of less than 2000 kg/cum is classified in the light concrete class. According to ACI (American Concrete Institute) Committee, light weight concrete is divided into three categories on the basis of its strength and density.

Properties	Lightweight Concrete Category		
	Low	Moderate	Structural
Unit weight (kg/m ³)	<1000	1000-1500	1500-2000
Compressive Strength (MPa)	0.70-2.00	2.00-15.00	16.00-42.00

Obilade and I.O.(2014) in their experimental study on rice husk as fine aggregates in concrete concluded that, there exists a high potential for the use of rice husk as fine aggregate in the production of lightly reinforced concrete. Weight-Batched Rice Husk Concrete and Volume-Batched Rice Husk Concrete showed similar trends in the variation of bulk density, workability and compressive strength. Loss of bulk density, workability and compressive strength is slightly higher for Weight-Batched Rice Husk Concrete than Volume Batched. They made the following recommendations: -The long term behaviour of rice husk concrete should be investigated. -Volume batching should be used in works involving rice husk. -Similar studies are recommended for concrete beams and slab sections to ascertain the flexural behaviour of light weight concrete made with rice husk. Sisman et al (2011) have analysed the effects of rice husk on concrete properties for farm buildings and arrived at the following conclusions, -The unit weight of the produced concrete samples varied between 1797-2268 kg/m³. When the RH amount in the mixture was greater than 15%, concrete should be classified as lightweight concrete with respect to their unit weights. -The compressive strength of the samples at 7 and 28 days ranged from 15.2-31.3 MPa and 18.1-37.5 MPa respectively. The concrete produced in their study were

defined as structural lightweight concrete when considering their unit weight and compressive strength. -The water absorption of the samples on the 28th day varied between 3.03-5.48% and the use of RH as an aggregate replacement increased water absorption. -The thermal conductivity decreased with increase in rice husk content. The thermal conductivity varied between 0.79-1.53 W/mK. Their research showed that the thermal conductivity of the RH aggregate concrete was approximately two times lower than that of an equivalent normal weight concrete. Tomas U. Ganiron Jr (2013) experimented on the effects of rice husk as substitute for fine aggregate in concrete mixture and made the following inferences:- -The results revealed that higher substitution amounts results into lower water absorption values due to more fineness property of RHA than cement. Adding 15% of RHA to the concrete, a reduction of 32.4% in water absorption value is observed. -The addition of RHA causes an increment in the compressive strength due to the capacity of the pozzolana towards fixing Ca (OH)₂ generated during the reactions of hydration of cement. All the replacements degrees of RHA increased the compressive strength. For a 7% of RHA, 15% of increment in compressive strength is observed. -According to the results of the splitting tensile test, all the replacement degrees of RHA research, achieved similar results. This may be realized that there is no interference of adding RHA in the splitting tensile strength. -The rice husk is applicable to concrete for interior concrete walls. -The wet weather conditions cause deterioration of husks that affect the stability of concrete. Based on their studies about Rice International Journal of Engineering Research ISSN: 2319-6890 (online), 2347-5013 (print) Volume No.4, Issue No.9, pp : 506-509 01 Sept. 2015 IJER@2015 Page 508 Husk, K.S. Low and C.K.(1997) and W.T. Tsai et al(2007) have concluded that RHA as pozzolona is an effective admixture for cement and used as additives to reduce corrosion and increase durability of concrete structures. M.Fang(2004) in his study concluded that the use of RHA contributed not only to the production of concrete of higher quality and lower cost but also reduced carbon-dioxide (CO₂) emissions from the production of cement. The partial replacement of cement by RHA would result in lower energy consumption associated with the production of cement. Premalal(2002) et al have made comparison of the mechanical properties of rice husk powder and hence concluded that chemical compositions of RHA are affected due to burning process. Silica content in the ash increases with higher temperature. RHA produced by burning rice husk between 6000C-7000C for 2 hours contains 90-95% SiO₂, 1-3% K₂O

III. CONCLUSION

Rice husk ash is one of the most active research areas that encompass a number of disciplines including civil engineering and construction materials. Rice husk ash is an agricultural waste product which is produced in large quantities globally every year and due to the difficulty involved in its disposal, RHA is becoming an environmental hazard in rice producing countries. India alone produces around 120 million tons of paddy per year, giving around 24 million tons rice husk per year and 6 million tons of rice husk

ash per year. As rice husk is piling up everyday, there is a pressure on rice industries to find a solution for its disposal. It is most essential to develop eco-friendly concrete from RHA. RHA can be used in concrete to improve its strength and other durability factors. From the review of above literatures from the various researchers, it can be well concluded that RHA can be used as cement in lightweight structural concrete preparation. Sustainable utilization would preserve conventional materials for future. To opt for green construction, RHA is a right choice, as it doesn't produce environmental pollution and accelerates speed of construction.

REFERENCES

- [1] Mehta, P.K. and Pirtz D. (2000), Use of rice husk ash to reduce temperature in high strength mass concrete, *ACI Journal proceedings*, 75; pp:60-63
- [2] Malhotra, V.M., P.K. and Mehta (2004), *Pozzolanic and cementitious materials*. London: Taylor & Francis.
- [3] Adeywi, A.P., Ola and B.F. (2005), Application of water works sludge as partial replacement for cement in concrete production, *Science Focus Journal*, 10(1); pp:123-130.
- [4] Habeeb, G.A., Fayyadh, M.M. (2009), Saw dust ash concrete: the Effect of SDA Average Particle Size, Mechanical Properties and Drying Shrinkage. *Australian Journal of Basic and Applied Sciences*, 3(3); pp:1616-1622.
- [5] Lee, S.T., Moon, H.Y. and Swamy, R.N. (2005), Sulphate Attack and Role of Silica Fume in Resisting Strength Loss; *Cement and Concrete Composites*, Vol 27; pp:65-76.
- [6] Gunduz, L and I. Ugur (2004), The effects of different fine and coarse pumice aggregate/cement ratios on the structural Concrete properties without using any admixtures, *Cement Concrete Res*, 35; pp:1859-1864.
- [7] Khedari, J., B. Suttisonk, N. Pratinthong and J. Hirunlabh (2001), New lightweight composite construction materials with low thermal conductivity, *Cement Concrete Composite*, 23(No.1); pp:65-70.
- [8] Sari, D. and A.G. Pasamehmetoglu (2004), The effects of Gradation and Admixture on the Pumice Lightweight Aggregate Concrete. *Cement Concrete Res*, 35; pp:936-942.
- [9] Obilade, I.O. (2014), Experimental Study On Rice Husk As Fine Aggregates In Concrete; *The International Journal of Engineering and Science (IJES)*, Vol.3; pp:09-14.
- [10] C.B. Sisman, E. Gezer and I. Kocaman (2001), Effects of Organic Waste (Rice Husk) On The Concrete Properties For Farm Buildings; *Bulgarian Journal of Agricultural Science*, 17(No. 1); pp: 40- 48.
- [11] Tomas U. Ganiron Jr (2013), Effects of Rice Husk As Substitute for Fine Aggregate in Concrete Mixture; *International Journal of Advanced Science and Technology*, Vol. 58; pp:29-40
- [12] K.S. Low and C.K. Lee (1997), Quaternized Rice Husk as Sorbent For Reactive Dyes, *Bioresource Technology*; Vol.61(No.2); pp:121-125.
- [13] W.T. Tsai, M.K. Lee and Y.M. Chang (2007), Fast Pyrolysis of Rice Husk-Product Yield and Composition, *Bioresource Technology*, Vol.98(No.1); pp:22-28.
- [14] M. Fang (2004), Experimental Study on Rice Husk Combustion in a Circulating Fluidized Bed-Fuel Preprocessing Technology, *Vol.85(No. 11)*; pp:1273-1282.
- [15] H. Premalal, H. Ismail and A. Baharin (2002), Comparison of the Mechanical Properties of Rice Husk Powder Filled Polypropylene Composites With Talc Filled Polypropylene Composites, *Poly-mer Testing*, Vol.21(No.7); pp:833-839.
- [16] V.M. Srivastava, I.O. Mall and I.M. Mishra (2006), Characterization of Mesoporous Rice Husk Ash (RHA) and Adsorption Kinetics of Metal Ions from Aqueous Solution onto RHA, *Journal of Hazardous Materials*, Vol.134(No.1); pp:257-267.
- [17] A.H. Mahvi, A. Maleki and A. Eslami (2004), Potential of Rice Husk and Rice Husk Ash for Phenol Removal in Aqueous Systems, *American Journal of Applied Science*, Vol. 1(No.4); pp:321- 326.
- [18] T.G. Chuah (2005), Rice Husk as a potentially Low Cost BioSorbent for Heavy Metal and Dye Removal: An overview, *Desalination*, Vol.175(No.3); pp:315-316.
- [19] Prof. Kumar R. Sathish (2012), Experimental Study On The Properties Of Concrete Made With Alternate Construction Materials, *International Journal of Modern Engineering and Research*, Vol.2; pp:3006-3012.
- [20] Singh Smita (Research Scholar) & Mr. Kumar Dilip (Asst. Prof.) (2014), Alternate and Low Cost Material- Rice Husk Ash (RHA), *International Journal of Innovative Research in Advance Engineering*, Vol.1; pp:214-218.
- [21] S.I. Khassaf, A.T. Jasim, F.K. Mahdi (2014), Investigation of the properties of concrete containing RHA to reduce seepage in canals; *International Journal of Scientific and Technology Research*, Vol.3; pp:348-354.
- [22] Sheth Ananya, Goel Anirudh, Pai Venkataram B.H. (2014), Properties of concrete on replacement of coarse aggregates and cementitious materials with Styrofoam and Rice Husk Ash respectively; *American Journal of Engineering and Research*, Vol.3; pp:268-271