

Effect of Different Types of Water on Strength of Concrete

Ms Nishigandha Chandne¹ Dr. Shirgire Anil²

¹PG Student ²Associate Professor

^{1,2}Department of Civil Engineering

^{1,2}JSPM's Imperial College of Engineering & Research, Wagholi, Pune, India

Abstract— This exploration examined the impact of various kinds of blending water on the compressive strength of cement. It investigated the impact of debasements, for example, salts of sodium, manganese, tin, zinc, copper and lead on the compressive strength of cement. The impacts of the presence of some different contaminations like residue and suspended particles on solid strength were additionally explored. Compressive strength test was completed on the blocks and the discoveries were genuinely handled. The outcomes demonstrated that wellsprings of water utilized in blending concrete essentially affect the compressive strength of the subsequent cement. It finished up by recommending that waterway water could be utilized for blending where faucet water is scant. Be that as it may, different properties, for example, sturdiness and shrinkage ought to be considered before use.

Keywords: Strength, Durability, Properties, Compressive

I. INTRODUCTION

If the waste water is utilized for some other domestic purposes it leads to a lot of human illness in their study haven given the impact of this problem in detail. To minimize these problems the waste water can be used for construction work without affecting the surrounding environment. By utilization of this water, water scarcity can be reduced. On the off chance that the waste water is used for some other homegrown purposes it prompts a ton of human sickness in their examination safe house given the effect of this issue in detail. To limit these issues the waste water can be utilized for development work without influencing the general climate. By usage of this water, water shortage can be decreased. Concrete for the most part addresses 12-14% of solid weight. It has a functioning impact in the combination. During the solidifying cycle, it produces shrinkage and warmth dispersal marvels which lead to material breaking. Water is a significant element of concrete as it effectively partakes in the synthetic response with concrete. Since it assists with shaping the strength giving concrete gel, the amount and nature of water is needed to be investigated cautiously. It has been examined enough about the amount of blending water however so far the nature of water has not been talked about. Practically speaking, frequently extraordinary control on properties of concrete and total is practiced yet the control on the nature of water is regularly dismissed. Since nature of water influences the strength, it is vital for us to go into the immaculateness and nature of water. In the current work, the blend extent is planned according to IS 10262 for M20 evaluation of cement. As there are such countless sorts of nature of water are accessible specifically faucet water, well water, bore well water, squander water and so forth every one of these kinds of water were utilized for making the solid blocks, example of size 150mm × 150mm × 150mm according to Indian standard were tried at 7 days 21 days and 28 days to discover compressive strength.

A. Advantages & Objectives

- 1) Utilizing of waste water for making concrete lessens the heap on water treatment measure, by evading the essential treatment measures screening, settling, air circulation and others.
- 2) By looking at compressive test outcomes, we can investigate what various sorts of water mean for's the strength of the solid.
- 3) Water tests are effectively accessible.

II. LITERATURE REVIEW

A. Effects of Wash Water on the Compressive Strength of Concrete Gabriel W. Cook

Because of the size of solid creation all through the world, there is potential for executing techniques that diminish the natural effect of solid cycles. One captivating arrangement is using solid wash water as blending water. Solid wash water is the water made by solid creation. On the off chance that wash water can be reused, this would give a protected removal of the water and save a great many gallons of consumable water each year (Indiana, 2014). For this to turn into a sensible choice for solid plants, it is significant that the wash water doesn't diminish the compressive strength of concrete, in any case the expense of extra cementitious materials to balance the compressive strength abatement will exceed any monetary advantage of reusing the wash water. Hence, the motivation behind this exploration project is to look at the impacts of wash water on the compressive strength of cement.

B. A Review of the Effects of Wastewater on Reinforced Concrete Structures in Nigeria K. A. Olonade*

This paper surveys the corruption component of wastewater on strengthened solid designs with the end goal of discovering what should be done to rescue these constructions. Potential deteriorating specialists in wastewater produced in Nigeria were recognized and normal corruption impacts were inspected. Recovery, preventive and remedial strategies were noted. While taking note of that helpless upkeep culture, absence of multidisciplinary research work and significant expense of support were central point liable for the high pace of crumbling. The paper, in this way, finished up with proposals that could be utilized to rescue these constructions from complete breakdown. One of such methodologies is to utilize admixtures, which could decrease the impact of acidic assault basic in wastewater solid constructions.

C. Effect of Treated Waste Water on Strength of Concrete

Ramkar A.P.1, Ansari U.S.

This examination manages the impact of various sort of treated waste water on properties of solidarity of cement, for example, compressive strength, elasticity and flexural

strength as for Potable water. The waste water test gathered from squander water treatment plant close to Shirdi. Water tests were utilized as Primary Treated Waste Water (PTWW), Secondary Treated Waste Water (STWW) which was examined for its substance properties in lab. In that utilization of solid blend of M30 the Potable water was completely supplanted with the PTWW, STWW and Domestic Waste Water. The tests directed are beginning and last setting time on concrete, Compressive strength, elasticity and flexural strength on solid which is contrasted and the blend of M30 of consumable water. The outcomes demonstrate that the underlying and last setting season of concrete was same as that of Potable water and STWW yet diminished for PTWW, for compressive strength it was expanded in STWW and homegrown waste water at longer length, for pliable and flexural strength tests was same outcomes along these lines, there was no any improvement in ductile and flexural strength by utilizing STWW.

III. OBJECTIVES

- To study the various sorts of water.
- To study the impact of various kinds of water of compressive strength, flexural strength, spilt elasticity on cement.
- To study the work is to analyse the compressive strength of cement for M20 grade by utilizing the various characteristics of water such a faucet water, bore well water, well water, squander water and so on
- Comparing arrangement of 3D shapes, shafts and chambers cast with various sorts of water and restoring and afterward discover the outcome.

To study the variety of M20 evaluation of cement by plotting diagram compressive strength, split elasticity, flexural strength as opposed to restoring time for 7,14.and 28 days.

IV. PRESENT INVESTIGATION


The trial work was done in two phases. In the main stage primer examinations, for example, consistency, explicit gravity, beginning and last setting season of concrete and sifter investigation of fine totals and coarse totals and testing of nature of water were done on materials utilized. In the subsequent stage solid blend proportioning was done according to the draft code (IS: 10262-2009) for M-20 grade Concrete and cubes, beams and cylinders were cast with three different sources of water [Potable water (PW), Sewage water (SW) and Ground water (GW)] and tested. The cubes beams and cylinders were tested properly in uniaxial compressive testing machine, Rebound Hammer Value, flexural testing machine and split tensile testing machine at the age of 7, 14 and 28days.

Average compressive strength NDT value (SRH)

SI NO	WATER TYPE	7 days	14 days	28 days
1	POTABLE WATER	14.90	18.00	23.00
2	SEWAGE WATER	9.00	12.50	16.00

3	GROUND WATER	15.50	16.50	20.10
---	--------------	-------	-------	-------


Table 1: Compressive strength results using Schmidt Rebound Hammer



Graph 1: Compressive strength results using SRH Average compressive strength fck, Nmm²

SI no	Water types	7 days	14 days	28 days
1	Potable water	14.50	17.50	22.50
2	Sewage water	10.20	13.10	15.00
3	Ground water	14.30	16.10	20.85


Table 2: Compressive strength Results using Compression Testing Machine



Graph 2: Compressive strength results using

SI no	Water types	7 days	14 days	28 days
1	Potable water	2.50	2.80	3.15
2	Sewage water	2.00	2.35	2.80
3	Ground water	2.55	2.70	3.00

Table 3: Flexural strength Test Results




Graph 3: Flexural strength test results

Average split tensile strength fck, Nmm²

SI no	Water type	7 days	14 days	28 days
1	Potable water	1.40	1.70	2.35
2	Sewage water	1.00	1.30	1.55
3	Ground water	1.50	1.55	2.00

Table 4: Split Tensile strength Result



Graph 4: Split tensile strength results

Characteristics	Potable water	Ground water	Sewage water
pH	8.2	6.6	10.2
Total dissolved solids	580mg/l	246mg/l
Total hardness	328mg/l	690mg/l
Nitrates	35mg/l	75mg/l	0.5mg/l
Chlorides	150mg	175mg/l	210mg/l
Total Suspended solids	270mg/l

Table 5: Tests on Water Samples for different Parameters

V. RESULTS AND DISCUSSIONS

From the present study the following observations are made:

- 1) Potable water suits the requirements of water to be used for construction activity results in increase of Compressive, Flexural and Split tensile strength of concrete compared to other sources of water.
- 2) It is observed that there is an increase of 33.34% in compressive strength of potable water concrete when compared to concrete prepared with sewage water.
- 3) It is observed that there is an increase of 11.12% in Flexural strength of potable water concrete when compared to concrete prepared with sewage water.
- 4) It is observed that there is an increase of 14.89% in Split tensile strength of potable water concrete when compared to concrete prepared with sewage water.

VI. CONCLUSIONS

From the present study, the following conclusions are drawn,

- 1) If the pH value of water increases the strength in concrete decreases substantially.
- 2) Because of high suspended solids and pH present in sewage water, the calcium Silicate Hydrate (C-S-H) which is responsible for strength in concrete gets deteriorated and weakens the concrete.

REFERENCES

- [1] Al-Manaseer, A.A., Haug, M.D. & Naseer, K.W. (1988) Compressive Strength of concrete containing fly ash, brine and admixture, American Concrete Institute, Material Journal, 85(2): 109-116.
- [2] Akinkulore et.al. (2007). "The influence of salt water on the compressive and engineering and applied science. 2007; 2(2); 412-415.
- [3] Cement Concrete & Aggregates Australia. "Use of Recycled Water in Concrete Production" August 2007.

- [4] Donald F. Griffin and Robert L. Henry "The effect of salt in concrete on compressive strength, water vapor transmission, and corrosion of reinforcing steel" Y-R007-05-01 -012.
- [5] I.S. 10262-2009: Recommended guidelines for concrete mix design. Bureau of Indian Standards, New Delhi.